

GRAPHISTRENGTH® C M4-30

POLYETHYLENE MASTERBATCH

TECHNICAL DATA SHEET

Description:

Graphistrength® C M4-30 is a Multi Wall carbon Nanotubes (MWCNT) concentrate that is used as an additive for polyolefin based materials. It contains 30 wt% of MWCNT perfectly dispersed in low-density polyolefin matrix. Graphistrength® C M4-30 contains no processing aid or other additives.

Graphistrength® C M4-30 is well suited for the production of semi conducting and conducting polyolefin based compounds.

Graphistrength® C M4-30 is provided in pellet form with the following key characteristics:

Property	Method	Unit	Typical value ⁽¹⁾
MWCNT content	TGA	wt%	30.0 ⁽²⁾
Moisture content	Karl-Fisher	wt%	0.05-0.15

⁽¹⁾ Data not intended for specification purposes

⁽²⁾ Graphistrength® C M4-30 contains MWCNT with purity > 90 %


Benefits and applications:

Graphistrength® C M4-30 is generally diluted in low and high-density polyethylene and functional polyolefins. Typical final MWCNT loadings in the final compounds are in the range 1 to 15 wt% depending on the host matrix characteristics, the targeted performances, processing methods and conditions.

The typical electrical resistivity that can be achieved is in the range 1 – 10⁸ ohm.cm as shown in the percolation plot below. The ESD properties obtained with Graphistrength® C M4-30 are outstandingly consistent and uniform.

Typical percolation curve for extruded strips

CM4-30 compounded with LDPE (injection grade, Melt Flow Rate - 26 g/10 min)
in twin screw extruder of D25, L/D-36



The resistivity is also depending on melt viscosity of the host matrix and process conditions. The percolation curve is normally shifted to lower CNT content for **foams, molded articles, compounds with mineral fillers**, articles obtained by **rotomolding** etc. Higher load of CNT for similar resistivity is needed for **films, extruded layers** as in **cables, pipes, fluid lines, textile yarns** etc.

Thanks to their low loading, and very small size, Graphistrength® MWCNT offer several additional advantages: smooth surface aspect, low increase in density and, high preservation of the neat matrix's ductility and mechanical properties, while enhancing thermo-mechanical properties. With low particulate generation, Graphistrength® MWCNT are also ideal additives for applications where cleanliness is key.

Dilution and processing guide

For optimal dispersion in **high flow rate polyolefins** (VLDPE, LDPE, HDPE, EVA, EDA, others), the use of a twin screw co-rotative extruder of L/D > 25 is recommended. The melting zone and the first mixing zone should be heated to temperature close to the melting point of the host matrix (120°C for LDPE for example). The last heating zones and the die should be regulated at the highest temperature level recommended in the process conditions of the host matrix (240°C for LDPE).

In the case of **viscous extrusion grades** the use of single screw compounding lines is acceptable. This type of equipment may also be used in two steps: 1) dilution by half in the host polyolefin to get 15 % of CNT and 2) further dilution to desired CNT content. This method is recommended when no twin screw available. For low melt temperature functional polyolefins and thermoplastic elastomers internal mixers can also be used.

Packaging and Storage:

Graphistrength® C M4-30 is provided in lined bags of 5 kg or 25 kg net. The product is indefinitely stable in its unopened original packaging when stored at normal temperatures.

Graphistrength® C M4-30 may absorb water if exposed for long periods of time to the atmosphere. In this case, the pellets must be dried at 80 °C for 2 hours before using.

Safety and Handling:

Graphistrength® C M4-30 is provided in pellet form where MWNT are strongly embedded.

Graphistrength® C M4-30 doesn't present any specific health risk when using in thermoplastic processing.

Consult the product MSDS for additional information on properties, hazards and handling.

Contacts:

- www.graphistrength.com
- **Europe**
Arkema France –
Tel.: + 33 (0)5 59 92 66 07
- **Japan**
Arkema K.K. –
Tel.: + 81 (0)75 326 7515
- **North America**
Arkema Inc. –
Tel.: + 1 610 878 6992

The information contained in this document is based on trials carried out by our Research Centers and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing, or use of the product or products concerned - which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

The statements, technical information, and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials, or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See MSDS for Health & Safety Considerations.

Arkema – 420, rue d'Estienne d'Orves – 92705 COLOMBES Cedex – France

Tel.: + 33 1 49 00 80 80 - Fax: 33 1 49 00 83 96

www.arkema.com

www.graphistrength.com

ARKEMA
INNOVATIVE CHEMISTRY